



升华集团德清华源颜料有限公司  
SHENGHUA GROUP DEQING HUAYUAN  
PIGMENT CO., LTD.



## TECHNICAL DATA

Edition of: 2010-12-9

<b>Trade name</b>	Iron oxide yellow			
<b>Type</b>	P-586			
<b>REACH</b>	Registration No. 01-2119457554-33-0014			
<b>Chemical name</b>	Iron hydroxide oxide ( $\alpha$ -FeOOH)			
<b>Delivery form</b>	Powder			
<b>Colour index</b>	Pigment yellow 42 (77492)			
<b>CAS No./EC No.</b>	20344-49-4/243-746-4			
<b>Specifications</b>	Contents ( $\alpha$ -FeOOH)	%	$\geq 86$	ISO1248
	Oil absorption	ml/100g	25~35	ISO787-5
	Res. on 325 mesh	%	$\leq 0.3$	ISO787-7
	Water soluble salts	%	$\leq 0.3$	ISO787-3
	Moisture	%	$\leq 1.0$	ISO787-2
	pH value		3~7	ISO787-9
	Ignition loss (1,000°C, ½ h)	%	$\leq 14$	DIN55913
	Bulk density	g/cm <sup>3</sup>	0.7~1.0	ISO787-11
	Specific gravity	g/cm <sup>3</sup>	4.1	ISO787-10
	Particle size BET	$\mu\text{m}$	0.1x0.6	Electron Micrographs
	Dispersibility (Hegman)	$\mu\text{m}$	20/25/30	ISO787-20
	Tinting Strength (Compared with Standard)	%	95~105	ISO787-24
	Color Difference $\Delta E$ (Compared with Standard)		$\leq 1.0$	ISO787-1
<b>Sales packing</b>	In 25kg paper bag/900kg bulk bag then palletized			
<b>Transport &amp; Storage</b>	Protect against weathering / Store in a dry place			
<b>Safety</b>	The product is not classified as hazardous under EC 1907/2006 & EC 1272/2008			

Unit C, 11 Floor, Baima Mansion, Miduqiao Road, Hangzhou, 310005 China

Tel: +86 (571) 85 81 21 60 Fax: +86 (571) 85 81 21 61

E-mail: [info@ironoxide.com.cn](mailto:info@ironoxide.com.cn) <http://www.ironoxide.com.cn>